



GCC of America

600 S. Cherry Street, Suite 1000, Glendale, CO 80246
 Sales (303) 739-5900, Customer Service (800) 225-5422

MATERIAL CERTIFICATION REPORT

Plant: Trident
Address: 4070 Trident Road
 Three Forks, MT 59752
Contact: Zach Gill
Phone: (406) 285-3988

Cement Type: 1157 GU / 595-1L
Date Issued: 6-Aug-18
Production Period: 1-Jul-18
To: 31-Jul-18

STANDARD REQUIREMENTS ASTM C150/AASHTO M85/ASTM C1157

CHEMICAL			
Item	ASTM Test Method	ASTM C150 Spec. Limit	Test Result
SO ₃ (%)	C114	3.0 max ^A	2.4
Loss On Ignition (%)	C114	10.0 max	5.3

PHYSICAL				
Item	ASTM Test Method	ASTM C150 Spec. Limit	ASTM C1157 Spec. Limit	Test Result
Air Content (%)	C185	12 max	12 max	8
Blaine Fineness (m ² /kg)	C204	260 min	-	438
Residue 45 µm (No.325) Sieve (%)	C430	-	-	2.7
Autoclave Expansion (%)	C151	0.80 max	0.80 max	0.01
Compressive Strength				
3 days, MPa (psi)	C109	12.0 (1740) min	13.0 (1890) min	28.3 (4110)
7 days, MPa (psi)	C109	19.0 (2760) min	20.0 (2900) min	36.9 (5350)
28 days, MPa (psi) ^C	C109	28.0 (4060) min	28.0 (4060) min	44.1 (6400)
Time of Setting, Initial Vicat (min)	C191	45 min / 375 max	45 min / 420 max	138
Mortar Bar Expansion (%)	C1038	0.020 max	0.020 max	-

ADDITIONAL DATA					
Type	Limestone	Test Method	Base Phase Composition	ASTM Test Method	Test Result

OPTIONAL REQUIREMENTS ASTM C150/AASHTO M85/ASTM C1157

CHEMICAL			
Item	ASTM Test Method	ASTM C150 Spec. Limit	Test Result
Equivalent Alkalies (%)	C114	0.60 max	0.41

PHYSICAL				
Item	ASTM Test Method	ASTM C150 Spec. Limit	ASTM C1157 Spec. Limit	Test Result

^A It is permissible to exceed the specification limit provided that ASTM C1038 Mortar Bar Expansion does not exceed 0.020 % at 14 days.

^C Test result of prior month

GCC of America Cement is warranted to conform at the time of shipment with current ASTM C150/AASHTO M85/ASTM C1157. No other warranty is made or implied. Having no control over the use of its cements, GCC of America does not guarantee finished work.